



THE SEWING THREAD MAKERS

CALIPS

Quality Control performance results on Chemical tests

Sewing Thread Spun Polyester SSP
Ticket's n°.: 120, 100, 80, 50, 36, 25.

Chemical Tests Description	Standard	Staining				Colour Range
		Light Colours	Median Colours	Dark Colours	Special Colours	
Wash Fastness	ISO 105 C06 (B2S 50°C)	4-5	4-5	4	3-4	4-5
Water Fastness	ISO 105 E01	4-5	4-5	4	3-4	4-5
Alkaline Perspiration Fastness	ISO 105 E04	4-5	4-5	4	3-4	4-5
Ácid Perspiration Fastness	ISO 105 E04	4-5	4-5	4	3-4	4-5
Dry Cleaning Fastness	ISO 105 D01	NA	NA	NA	NA	4-5
Chlorine Water Fastness	ISO 105 E03	NA	NA	NA	NA	4-5
See Water Fastness	ISO 105 E02	4-5	4-5	4-5	4-5	4-5
Dry Rub Fastness	ISO 105 X12	5	4-5	4-5	4-5	NA
Wet Rub Fastness	ISO 105 X12	4-5	4-5	4-5	4	NA
Light Fastness	ISO 105 B02	NA	NA	NA	NA	4
Contact Heat Fastness / Sublimation at 120°C	ISO 105 X11	5	4-5	4	4	4

NA = Not applicable

(*) The special colours included: Black, Deep colours and some fluorescent colours.

Care Codes Recomendaded

Relevant Notes



Wash maximum 40°C
Gentle program



Do not use Chlorine agents



Iron with median temperature
150°C



Possible Dry Cleaning
professional

Note: For complete the Care Label codes is very important included the security phrase in every garments or Embellishment: Keep way from fire.
The Dry method (Tumble Dry machine or Temperature Ambiance dry) need be analyzed just on the garment final with all details included.



www.lipaco.com

Leading the way for 30 Years

